```
L6
     ANSWER 19 OF 24 CA COPYRIGHT 2006 ACS on STN
     122:87744 CA
AN
     Entered STN: 18 Feb 1995
ED
TI
     Admixtures for cement, and cement compositions
     containing the admixtures
     Kyogoku, Yasuhiro; Kanamori, Shinji; Ida, Makio; Mihara, Toshio
IN
PA
     Denki Kagaku Kogyo Kk, Japan
     Jpn. Kokai Tokkyo Koho, 5 pp.
SO
     CODEN: JKXXAF
DT
     Patent
LA
     Japanese
IC
     ICM C04B022-12
     ICS C04B022-14; C04B024-26; C04B028-02; C04B028-22
CC
     58-1 (Cement, Concrete, and Related Building Materials)
FAN.CNT 1
                                            APPLICATION NO.
     PATENT NO.
                         KIND
                                DATE
                                                                   DATE
     -----
     JP 06256053
                                19940913
                                                                   19930301
                         A2
                                            JP 1993-39922
PRAI JP 1993-39922
                                19930301
CLASS
 PATENT NO.
                CLASS PATENT FAMILY CLASSIFICATION CODES
                ----
 JP 06256053
                ICM
                        C04B022-12
                        C04B022-14; C04B024-26; C04B028-02; C04B028-22
                ICS
                IPCI
                        C04B0022-12 [ICM,5]; C04B0022-14 [ICS,5]; C04B0024-26
                        [ICS,5]; C04B0028-02 [ICS,5]; C04B0028-22 [ICS,5]
    Th admixts. contain latent hydraulic binders, Ca fluoroaluminates, inorg.
AB
     sulfates, thickeners, and water reducing agents, and
     are mixed with cement to give the cement compns.
     Concrete prepared from a composition containing portland cement 56,
     fly ash 24, Ca fluoroaluminate 10, and II-type anhydrite
     10 weight parts 460, water 158.1, fine aggregate 889, coarse
     aggregate 741, and Darex Super 100PHX (water reducing
     agent) 6.9 kg/m3, with addition of Me cellulose 20, and air-entraining agent
     23 g/m3, had excellent workability and 3-, 7-, and 28-day compressive
     strength 260, 340, and 480 kg/cm2, resp.
     calcium fluoroaluminate sulfate cement; fly
     ash calcium fluoroaluminate concrete
IT
    Concrete
```

- Cement - flyash - water - water reducing again